

Amendments to the Claims:

This listing of claims replaces all prior versions and listings of claims in the application:

Listing of Claims:

1. (Currently Amended) A plastics pipe which comprises an inner core and an outer removable skin layer bonded thereto,  
the outer removable skin layer comprising a polymeric material, chosen for its physical and mechanical properties, and an adhesion-modifying additive,  
the adhesion-modifying additive being present in the skin layer in an amount such that ~~the adhesion~~ an adhesive bond of the skin layer to the inner core is sufficient to prevent substantial undesired relative movement between the skin layer and the core during installation, but insufficient to prevent the outer skin layer from being cleanly removed by peeling, at least at the ends of the pipe, and insufficient to cause a substantial reduction in the impact strength of the inner core, the adhesive bond between the skin layer and the inner core having a strength of from 0.2 N/mm to 2.0 N/mm, when measured by a rolling drum peel test as described in Appendix 1.

2. (Cancelled).

3. (Previously Presented) A plastics pipe according to claim 1, wherein the strength of the adhesive bond between the skin layer and the inner core is from 0.3 N/mm to 1.5 N/mm, when measured by a rolling drum peel test as described in Appendix 1.

4. (Previously Presented) A plastics pipe according to claim 1, in which the strength of the adhesive bond between the skin layer and the inner core is such that the impact strength of

the composite pipe is at least 50%, preferably 75%, of the impact strength of the inner core without the skin layer.

5. (Previously Presented) A plastics pipe according to claim 1, in which the inner core comprises polyethylene.

6. (Previously Presented) A plastics pipe according to claim 1, wherein the skin layer comprises a propylene homo-or co-polymer, a propylene block co-polymer, or a propylene random polymer.

7. (Original) A plastics pipe according to claim 6, wherein the skin layer comprises a propylene block co-polymer.

8. (Previously Presented) A plastics pipe according to any claim 1, in which the inner core comprises polyethylene and the skin layer comprises a propylene co-polymer and wherein the impact strength of the pipe is greater than 300 joules, when measured using the method of EN1411:1996 at a temperature of -10°C using a 90mm tup for impacting the pipe.

9. (Previously Presented) A plastics pipe according to claim 1, wherein the skin layer comprises an adherent polymeric material and an appropriate amount of an adhesion-reducing additive.

10. (Original) A plastics pipe according to claim 9, wherein the adhesion-reducing additive in the skin layer is present in an amount from 0.5% to 10% by weight.

11. (Previously Presented) A plastics pipe according to claim 9, wherein the adhesion-reducing additive is an ester of a polyhydric alcohol.

12. (Original) A plastics pipe according to claim 11, wherein the polyhydric alcohol is glycerol.

13. (Previously Presented) A plastics pipe according to claim 11, wherein the ester is a fatty acid ester.

14. (Previously Presented) A plastics pipe according to claim 11, wherein the adhesion-reducing additive is glycerol monostearate.

15. (Previously Presented) A plastics pipe according to claim 1, which comprises an inner core of polyethylene and a skin layer of a propylene block copolymer comprising from 2% to 4% of a glycerol ester.

16. (Previously Presented) A plastics pipe according to claim 1, wherein the adhesion-reducing additive is a fatty acid amide.

17. (Original) A plastics pipe according to claim 16, wherein the fatty acid amide is stearamide or erucamide.

18. (Original) A plastics pipe according to claim 16, wherein the fatty acid amide is ethylene-bis-stearamide.

19. (Previously Presented) A plastics pipe according to claim 1, wherein the skin layer has a thickness within the range from 0.2mm to 2.0mm.

20. (Previously Presented) A plastics pipe according to claim 1, wherein the ratio of the external diameter of the pipe to the thickness of the skin layer is from 100 to 800.

21. (Previously Presented) A plastics pipe according to claim 1, wherein the strength (in N per mm of width) of the skin layer exceeds the peel strength (in N per mm width) of the adhesive bond between the outer removable skin layer and the inner core.

22. (Cancelled).

23. (Currently Amended) A method for the production of a plastics pipe comprising an inner core and an outer removable skin layer bonded thereto, the outer removable skin layer comprising a polymeric material chosen for its physical and mechanical properties, and an effective amount of an adhesion-modifying additive, which method comprises co-extruding molten polymeric materials forming the inner core and the outer removable skin layer from one or more extruder dies, bringing the molten polymeric materials together and allowing them to cool, such that, on cooling, ~~the~~ adhesion of the skin layer to the inner core is sufficient to prevent substantial undesired relative movement between the skin layer and the core during installation of the pipe, but insufficient to prevent the skin layer from being cleanly removed by peeling, at least at the ends of the pipe, and insufficient to cause a substantial reduction in the impact strength of the inner core, the adhesion between the skin layer and the inner core having a strength of from 0.2 N/mm to 2.0 N/mm, when measured by a rolling drum peel test as described in Appendix 1.

24. (Currently Amended) A method according to claim 23, wherein the polymeric materials of the inner core and the outer removable skin layer are extruded simultaneously and brought together ~~whilst~~ while still molten.

25. (Cancelled)

26. (Previously Presented) A method of making a joint to a plastics pipe according to claim 1, or of joining two such plastics pipes, which comprises peeling the skin layer from the

region or regions of the pipe to be joined, to expose a clean surface suitable for electrofusion jointing, installing an electrofusion fitting over the clean surface or surfaces of the pipe or pipes and activating the electrofusion fitting to fuse the region or regions of the pipe or pipes thereto.

27. (Previously Presented) A plastics pipe according to claim 9, wherein the adhesion-reducing additive is selected from the group consisting of acid anhydrides, ethoxylated amines, ethoxylated esters and polybutylene.